

MATERIAL SAFETY DATA SHEET

SECTION 1 PRODUCT IDENTIFICATION	
<b>Product Identification</b>	
Lithium-Ion Rechargeable Battery	
Nominal Voltage(V):	3.2
Cell P/N:	LP44147185AC
Minimum Cell Capacity(Ah):	78
Cell UL NO:	
Customer P/N:	N/A
<b>Manufacture Identification</b>	
Tianjin Lishen Battery Joint-Stock CO. LTD.	
6 Lanyuan Road, Huayuan Hi-Tech	
Industry Park, Tianjin 300384, China	
<a href="http://www.lishen.com.cn">Http://www.lishen.com.cn</a>	
86 - 22 - 83710366	
Phone Number (For Information)	
86 - 22 - 83710366	
Emergency Phone Number Telex'	
86 - 22 - 83710366	
Note: Blank spaces are not permitted. If any item is not applicable or no information is available, the space must be marked to indicate that.	

SECTION 2 HAZARDS IDENTIFICATION	
<b>Primary Routes of Entry</b>	<input type="checkbox"/> Inhalation <input type="checkbox"/> Ingestion <input type="checkbox"/> Skin Absorption <input type="checkbox"/> Eye contact
<b>Health Hazards</b>	<b>ACUTE AND CHRONIC</b> All chemicals are contained in a sealed can. Risk of exposure occurs only, if the battery is mechanically or electrically abused (mechanical, thermal, electrical), which leads to the rupture of the battery container. Electrolyte leakage, electrode materials reaction with moisture/water or battery vent/fire may follow, depending upon the circumstances.
<b>Medical Conditions Generally Aggravated By Exposure</b>	
An acute exposure will not generally aggravate any medical condition.	
<b>Symptoms of Exposure</b>	Skin contact, no effect under routine handling and use.
<b>Eye Contact</b>	No effect under routine handling and use
<b>Skin Contact</b>	No effect under routine handling and use
<b>Ingestion</b>	No effect under routine handling and use
<b>Inhalation</b>	No
<b>Reported as carcinogen</b>	Not applicable

SECTION 3 COMPOSITION & INFORMATION ON INGREDIENTS								
Equivalent lithium content per cell (g)			23.400	OSHA	ACGIH	CAS Number	OTHER LIMITS	
COMPONENTS-Chemical Name and Common Names (Hazardous Components 1% or greater, Carcinogens 0.1% or greater)			%	PEL	TLV		RECOMMENDED	
<b>Hazardous Ingredients:</b>	<b>Cathode active material</b>	<b>Lithium iron phosphate</b>	25.69%			12190-79-3		
	<b>Anode active material</b>	<b>Graphite Carbon</b>	14.43%			7782-42-5		
	<b>Electrolyte</b>	<b>LiPF<sub>6</sub></b>	<b>13.3%</b>	2.76%			21324-40-3	
		<b>Others</b>	<b>86.7%</b>	18.01%				
	<b>AL foil</b>	<b>Aluminum</b>		4.92%			7429-90-5	
	<b>Cu foil</b>	<b>Copper</b>		8.71%			7440-50-8	
	<b>Separator</b>	<b>Polypropylene</b>		3.7%			9003-07-0	
		<b>Polyethylene</b>					9002-88-4	
	<b>Cap</b>	<b>Copper</b>		7.1%			7440-50-8	
		<b>Aluminum</b>					7429-90-5	
<b>Can</b>	<b>Aluminum</b>		8.74%			7429-90-5		
<b>Others</b>			5.93%					
<b>Total</b>			100%					

SECTION 4 FIRST-AID MEASURES	
<b>If exposure to internal materials in cell due to damaged outer casing, the following actions are recommended.</b>	
<b>Eye Contact</b>	In case of eye contact, flush with lot of water for 15 minutes, and get medical help.
<b>Skin Contact</b>	In case of skin contact with contents of battery, flush immediately with water.
<b>Inhalation</b>	In case of light inhalation ,move to an area with flash air immediately, if irritation persists, get medical help.
<b>Ingestion</b>	In case of ingestion, drink milk/water to induce vomiting and wash out, get medical help.



<b>SECTION 5 FIREFIGHTING MEASURES</b>		
<b>Extinguisher Media:</b> CO <sub>2</sub> or dry chemical powder		
<b>Special Fire-Fighting Procedures:</b> In case of fire in cell original containers, use CO <sub>2</sub> or dry chemical extinguisher; For fire in an adjacent area, water can be used.		
<b>SECTION 6 ACCIDENTAL RELEASE MEASURES</b>		
<b>On Land:</b> Place material into suitable containers, If the skin has come into contact with the electrolyte, it should be washed thoroughly with water, Sand or earth should be used to absorb any exuded material. Seal leaking battery and contaminated absorbent material should be treated by local regulation, and call local fire/police department to ask for help.		
<b>In Water:</b> If possible, remove from water far from body in special fixture, and call local fire/police department to ask for help		
<b>SECTION 7 HANDING AND STORAGE</b>		
<b>Handling:</b> Take all precautions mentioned in this document and operate the battery within the temperature ranges as follows: Charge: 0 °C~45 °C; Discharge: -20 °C~60 °C; Storage:-20 °C~35 °C. No special protective clothing required for handling individual cells in corrective operational method. Improper handling of lithium ion battery may result in injury or damage from electrolyte leakage, heating, ignition or explosion.		
<b>Storage:</b> Store the battery in a cool, drying place, without chemical vapor or excessive humidity.		
<b>SECTION 8 EXPOSURE CONTROLS &amp; PERSONAL PROTECTION</b>		
<b>Engineering Controls:</b> keep away from heat and open flame, prevent hard & sharp thing penetration, store in a cool & dry place.		
<b>Personal Protection:</b> Respiratory Protection: Not necessary under normal operations condition. SCAB required in the event of a fire. Eye/Face Protection: Not necessary under normal operation condition. Glove protection: Not necessary under normal operation condition Foot Protection: Steel toed shoes recommended for Large container handling.		
<b>Ventilation to Be Used</b>	<input type="checkbox"/> <b>Local Exhaust</b> Not necessary under conditions of Normal use.	<input type="checkbox"/> <b>Mechanical (General)</b> Not necessary under conditions of Normal use.
	<input type="checkbox"/> <b>Other (Specify)</b> Not necessary under normal operation conditions.	<input type="checkbox"/> <b>Special</b> Not necessary under conditions of Normal use.
<b>Other Protective Clothing and Equipment</b> Not necessary under normal operation conditions.		
<b>Hygienic Work Practices</b> Not necessary under normal operation conditions.		
<b>SECTION 9 PHYSICAL /CHEMICAL PROPERTIES</b>		
<b>Specific Gravity (H<sub>2</sub>O=1):</b> LiFeO <sub>4</sub> :2.80 Graphite:2.0~2.2		
<b>Melting Point:</b> LiFeO <sub>4</sub> : > 1000°C Graphite:3500-3900°C		
<b>Appearance and Odor:</b> LiFeO <sub>4</sub> is a gray odorless powder; Graphite is a black or odorless powder; Organic solvent is a colorless liquid; Lithium salt is a white, crystalline and odorless powder.		
<b>SECTION 10 STABILITY &amp; REACTIVITY DATA</b>		
<b>Stability</b> <input checked="" type="checkbox"/> Stable <input type="checkbox"/> Unstable	<b>Conditions to Avoid:</b> Do not heat or incinerate the battery, Never impact, pierce or crush the battery. Do not disassemble or modify the battery, Do not charge the battery under high temperature conditions such as near a fire or in the direct sunlight. Do not short-circuit the battery by connect the positive and negative terminals with a metal material. Do not allow the battery to get wet or be immersed in water.	
<b>Incompatibility (Materials to Avoid)</b> Water, salted water, other solvent with water		
<b>Hazardous Decomposition Products</b> N/A		
<b>Hazardous Polymerization</b> <input type="checkbox"/> May Occur <input checked="" type="checkbox"/> Will Not Occur	Conditions to Avoid	

<b>SECTION 11 TOXICOLOGICAL INFORMATION</b>																																						
This product does not elicit toxicological properties during routine handling and use.																																						
<b>SECTION 12 ECOLOGICAL INFORMATION</b>																																						
Cobalt and its compounds can pose a threat if released to environment. The detail information are showed in waste disposal method in Section 13 "Disposal Consideration".																																						
<b>SECTION 13 DISPOSAL CONSIDERATIONS</b>																																						
There is no contamination during normal operation and use. Lithium batteries should have their terminals insulated prior to disposal, do not throw away a used battery and provide them for recycling company.																																						
Open cells should be treated as hazardous waste. If the leakage or other material is Released, we should take actions as follows: Leave the area, allow the batteries to cool down, let the vapors to dissipate . Avoid skin and eye contact or inhalation of vapors. Remove spiller liquid with absorbent and incinerate after.																																						
Waste Disposal method Opened cells should be treated as hazardous waste. Incineration: incineration should never be performed by battery users but eventually by trained professionals in authorized facilities with proper gas and fumes treatment. Landfilling: According to the proper laws and regulations in different countries or areas, the battery should be buried deeply in the specified place; Recycling: Send to authorized recycling facilities to get Cu and Al, eventually through licensed waste carrier;																																						
<b>SECTION 14 Transportation</b>																																						
Lishen's LP44147185AC Lithium-Ion cells are considered to be "Rechargeable Lithium Ion Batteries" and meet the requirements of transportation by the United States Department of Transportation (DOT), International Civil Aviation Administration (ICAO), 2013 International Air Transportation Association (IATA), be assigned to Class 9 Dangerous Goods and consigned as UN 3480 (Lithium ion batteries). The mentioned batteries are complied with the special provision, Section IA of PI965.																																						
<b>14.1 The requirement of air transportation</b>																																						
The lithium battery should according with the International Air Transport Association (IATA DGR 54 edition) requirements for transportation. IATA 54th defined the lithium battery as Class 9 Dangerous Goods and require class II packaging. Do not damage or mishandle this package. If package is damaged, batteries must be quarantined, inspected, and repacked. Cells and batteries identified by the manufacturer as being defective for safety reasons, or that have been damaged, that have the potential of producing a dangerous evolution of heat, fire or short circuit are forbidden for transport. Waste lithium batteries and lithium batteries being shipped for recycling or disposal are prohibited from air transport unless approved by the appropriate national authority of the State of origin and the State of the operator. The lithium battery should pass the UN38.3 test, if the battery can not pass the testing, it can not transport, should redesign. If the battery through the test, for the lithium battery only, follow the UN3480 and the packing requirements for PI965, for the lithium battery which installed in equipment, follow the UN3481 and the packing requirements for PI967. The lithium battery testing meets all requirements under UN Manual of Tests and Criteria Part III, subsection 38.3.																																						
<b>14.2 The requirement of ocean shipping</b>																																						
According to International Maritime Dangerous Goods Code to transport and according to the requirements of UN NO3480/3481 to management the goods. International Maritime Dangerous Goods Code require the dangerous goods operators on shore should be trained. The untrained operators can not handle the dangerous goods without training person guide. The goods should accord with Test and standard manual test standards. Firmly installation, mutual isolation, avoid short circuits. If the package contain more than 24 lithium batteries of more than 12 lithium battery packs, must provide the special program if package damage.																																						
<b>SECTION 15 REGULATORY INFORMATION</b>																																						
IATA DGR <input checked="" type="checkbox"/> Hazardous <input type="checkbox"/> Non-hazardous																																						
<b>SECTION 16 OTHER INFORMATION</b>																																						
There is no hazards in accordance with the UN recommendations test. (UN manual of tested and criteria 38.3)																																						
<table border="1"> <tr> <td>Cell Part Number</td> <td>LP44147185AC</td> </tr> <tr> <td>Nominal Voltage</td> <td>3.2V</td> </tr> <tr> <td>Minimum Cell Capacity</td> <td>78Ah</td> </tr> <tr> <td>Cell Mass</td> <td>2238g</td> </tr> <tr> <td>Equivalent Lithium Content</td> <td>23.4g</td> </tr> </table>		Cell Part Number	LP44147185AC	Nominal Voltage	3.2V	Minimum Cell Capacity	78Ah	Cell Mass	2238g	Equivalent Lithium Content	23.4g																											
Cell Part Number	LP44147185AC																																					
Nominal Voltage	3.2V																																					
Minimum Cell Capacity	78Ah																																					
Cell Mass	2238g																																					
Equivalent Lithium Content	23.4g																																					
<table border="1"> <thead> <tr> <th>Test NO</th> <th>Test Item</th> <th>Criteria</th> <th>Result</th> </tr> </thead> <tbody> <tr> <td>38.3.4.1</td> <td>Altitude Test</td> <td>No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing</td> <td>Passed</td> </tr> <tr> <td>38.3.4.2</td> <td>Thermal Test</td> <td>No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing</td> <td>Passed</td> </tr> <tr> <td>38.3.4.3</td> <td>Vibration</td> <td>No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing</td> <td>Passed</td> </tr> <tr> <td>38.3.4.4</td> <td>Shock</td> <td>No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing</td> <td>Passed</td> </tr> <tr> <td>38.3.4.5</td> <td>External Short Circuit</td> <td>External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.</td> <td>Passed</td> </tr> <tr> <td>38.3.4.6</td> <td>Impact</td> <td>External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.</td> <td>Passed</td> </tr> <tr> <td>38.3.4.7</td> <td>Overcharge</td> <td>No disassembly, and fire within seven days of this test.</td> <td>Passed</td> </tr> <tr> <td>38.3.4.8</td> <td>Forced Discharge</td> <td>No disassembly, and fire within seven days of this test.</td> <td>Passed</td> </tr> </tbody> </table>	Test NO	Test Item	Criteria	Result	38.3.4.1	Altitude Test	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed	38.3.4.2	Thermal Test	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed	38.3.4.3	Vibration	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed	38.3.4.4	Shock	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed	38.3.4.5	External Short Circuit	External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.	Passed	38.3.4.6	Impact	External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.	Passed	38.3.4.7	Overcharge	No disassembly, and fire within seven days of this test.	Passed	38.3.4.8	Forced Discharge	No disassembly, and fire within seven days of this test.	Passed		
Test NO	Test Item	Criteria	Result																																			
38.3.4.1	Altitude Test	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed																																			
38.3.4.2	Thermal Test	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed																																			
38.3.4.3	Vibration	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed																																			
38.3.4.4	Shock	No mass loss, leakage, venting, disassembly, rupture, and fire. OCV should not be less than 90% before testing	Passed																																			
38.3.4.5	External Short Circuit	External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.	Passed																																			
38.3.4.6	Impact	External temperature should not exceed 170degC. No disassembly, and fire within six hours of this test.	Passed																																			
38.3.4.7	Overcharge	No disassembly, and fire within seven days of this test.	Passed																																			
38.3.4.8	Forced Discharge	No disassembly, and fire within seven days of this test.	Passed																																			